



**ELASTOMERIC ACRYLIC CERAMIC**  
**BUS-KOTE™**  
**WATERPROOFING & INSULATING**  
**BUS - RECREATIONAL VEHICLE COATING**

**PRODUCT DATA**  
**#7740**  
**01/16/13**  
*superseding: 03/29/10*

**PRODUCT DESCRIPTION:**

**BUS-KOTE™** is a Matte Finish, Bright White, Elastomeric Acrylic, Reflective, Insulating and Soundproofing Ceramic, Waterproofing Bus & Recreational Vehicle Roof Coating. It is a waterborne, high build formula that possesses waterproofing, insulating and soundproofing properties that beautifies, protects and extends the life of most sloped surfaces. It forms a thick rubber like ceramic shield of protection that expands and contracts with varying hot and cold temperatures, plus excellent resistance to thermal shock. Unsurpassed in technology, **BUS-KOTE™** is an energy saving reflective coating that offers superior mildew resistance, ceramic insulation & soundproofing, excellent adhesion, U.V. ray reflectivity and a beautiful matte finish. An energy saving coating that combats the destructive environmental forces of nature. This easy to apply Bus and Recreational Vehicle Coating System will provide many years of durable protection and outstanding beauty. **BUS-KOTE™** offers a **7 YEAR LIMITED MATERIAL WARRANTY** when applied to manufacturer's specifications.

The **BUS-KOTE™** formula was initially designed as an insulating reflective coating for School Districts to use on the roofs of school buses with no air conditioning to help in lowering the interior temperatures of buses. This energy saving coating combines reflectivity and ceramic insulation to reduce interior temperatures when hot and make interior temperatures more constant when cold. It is formulated to resist over 100 M.P.H. wind driven rains.

**BUS-KOTE™ USES:**

Recommended for well draining, SLOPED Bus & Recreational Vehicle roof surfaces. **BUS-KOTE™** can also be used on a wide variety of other substrates including wood, shakes, plywood, clapboard, primed metal, galvanized, aluminum, tin, copper, asbestos, asphalt, urethane, polyester, primed styrofoam, fiberglass, built-up-roofs, rolled roofing, modified bitumen membranes, mineral surfaced roofing, primed synthetic or aluminum, adobe, slate, slab, properly prepared EPDM and various other substrates. For flat surfaces or limited ponding water situations inquire about **PERMAKOTE PLUS®**, Limited Ponding Water Roof Coating.

**SURFACE PREPARATION:**

A primer sealer coat of **BUS-PRIME™** should have been applied prior to the application of **BUS-KOTE™**. Apply only to a sound, completely dry surface. Leaks must be repaired before any coating is applied. If **BUS-PRIME™** primer was applied, it is essential that the primer surface is clean and dry and free of all moisture. If no primer was applied, prepare surface by thoroughly pressure washing with a water and chlorine mixture using at least 1500 P.S.I. to remove any previous coatings, dirt, grease and other foreign materials, especially mold, mildew and algae. **BUS-KOTE™** will resist mildew growth, but will not kill mildew already on the surface. Patch any holes, cracks, flashings, valleys, vents, etc., with **PERMAPATCH™**, a Waterproofing Caulk and Sealant. Tape & seal all seams with **PERMATAPE™**, a Polyester Fabric Tape.

**Metal:** Clean surface of all grease, oil and foreign matter before priming or coating. Rusted metal and uncoated ferrous metals must be primed with **METAL-PRIME RED-OX™**, a Red Iron Oxide Primer Sealer. Use a degreaser on galvanized or coated metals which have oils or surface treatments.

**Previously Coated Surfaces:** Check **BUS-KOTE™** adhesion on galvanized or coated metal or other previously coated surfaces by applying to a small area and evaluating after 48 hours. If lack of adhesion is present after evaluating, the surface must be sanded and **BUS-PRIME™** may be necessary. If applicable, use **METAL-PRIME RED-OX™** to spot prime the penetrated areas that are down to exposed bare metal.

**APPLICATION PROCEDURE:**

Stir well before using. Do not thin, use product as is. Mix multiple containers of color together for greater color consistency. Do not apply when temperatures are below 45 degrees Fahrenheit or when humidity is very high. Do not apply when coating will be subjected to rain or heavy dew before it has had enough time to dry (approximately 2 to 4 hours). Drying time will vary depending on temperature, humidity and location. Apply using brush, roller or spray. Spread coating uniformly. Spread Rate will vary depending on surface. Apply at 12 to 16 mils wet film thickness per coat. Wait at least 12 hours between coats. Two coats of **BUS-KOTE™** applied over a coat of **BUS-PRIME™** is required for the **7 YEAR LIMITED MATERIAL WARRANTY**.

**Airless Sprayers:** Use at least a 1 gallon per minute piston type airless sprayer with a minimum tip size of .025. Remove all line filters and gun filters before spraying.

**Clean Up:** Clean up all spills, tools and overspray immediately while the coating is still wet with warm soapy water.

Specialty

Ambient Temperature of 77°F and RH of 50%		<b>TECHNICAL SPECIFICATIONS:</b>	Rates & Times May Vary Beyond Specifications
FINISH:	Matte	SPREAD RATE:	100 to 150 sq. ft./gal.
COLOR:	White, Deep & Clear Base	DRY to TOUCH:	2 to 4 Hours
VEHICLE TYPE:	Copolymer Emulsion	RECOAT:	12 Hours
SOLIDS by WEIGHT:	64% +/- 2%	CURE TIME:	5 to 7 Days
SOLIDS by VOLUME:	37% +/- 2%	SIZES:	1 Gal., 5 Gal., 55 Gal.
V.O.C.'s (averages):	.39 lbs./gal. • 48.8 g/liter	GALLON WEIGHT:	11.7 lbs. +/- .3 lbs.
Information presented on this Data Sheet has been compiled from sources to be reliable, and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so.			

In Any Event Nationwide Protective Coating Manufacturers, Inc. will not be liable or responsible for any past, present or future leaks or any resulting consequential or incidental damages.



# MATERIALS HEALTH, SAFETY AND ENVIRONMENTAL DATA SHEET

**MSDS#:  
7740**

<b>Product Identification</b>	Product Name: <b>BUS-KOTE™</b> Product Code #: <b>7740</b> General Usage: Exterior Bus & Recreational Vehicle Coating General Description: Pigmented Latex Coating C.A.S. Number: None Established; Mixture	
<b>Manufacturer Information</b>	Manufacturer's Name: Nationwide Chemical Coating Mfrs., Inc. Address: 7106 24th Court East; Sarasota, FL 34243-3993 Emergency Telephone: 1-800-423-7264 or 941-753-7500 Information: 1-800-423-7264 or 941-753-7500 Web Site: www.nationwidecoatings.com E-Mail: info@natcoat.net Date Effective: January 1 <sup>st</sup> , 2005	
<b>Chemical and Physical Properties</b>	Color: White Physical State: Liquid Boiling Point: 212 Fahrenheit Specific Gravity (H <sub>2</sub> O=1): >1 Vapor Presence: about same as H <sub>2</sub> O Percent Volatile: 32-37% Evaporation Rate (Butyl Acetate=1): <1	Odor: Pungent Odor Odor Threshold: Unknown Melting Point: N/A Freezing Point: 32 Fahrenheit Solubility in H <sub>2</sub> O: Soluble pH (undiluted): 8 to 8.5 Vapor Density (Air=1): <1
<b>Fire Protection Information</b>	Decomposition/Combustion: Flash Point: Recommended Extinguishing Media: Flammable Limits:	N/A N/A; Does Not Burn N/A N/A
<b>Storage and Reactivity</b>	Hazardous Polymerization: Storage Conditions: Toxic Products Which May Form:	Will Not Occur Keep from Freezing None
<b>Transportation</b>	Hazard Classes: Hazard Labels: Hazard Determination: Shipping Containers: Shipping Class:	None; Not Hazardous Not Required MSD Sheet Varies Class 55; Water Based Paint
<b>Container Labeling</b>	Explanation of Unique Labeling System: None Used	

<b>Health Hazard Data</b>	<b>SHORT TERM EXPOSURE</b>	
	Route of Entry: Inhalation: Skin:  Eyes:  Ingestion:	Precautionary Treatment Expected None Expected None  Flush Immediately with large amounts of water for at least 15 minutes, holding eyelids open. Call a physician if irritation persists  Call a physician if significant amounts have been Swallowed. Give patient large amounts of water or milk for dilution.
	<b>LONG TERM EXPOSURE</b>	
	Carcinogen: Target Organ Effects: Other Health Hazards:	None None None Known
<b>Personal Protection</b>	Respiratory Protection: Protective Clothing: Ventilation: Other Protective Measures: Eye Protection:	No inhalation hazard expected None Required Local None Safety Glasses
<b>Spill or Leak Protection</b>	Accidental Release or Spill:  Neutralizing Chemical/Media:	Collect liquid or solidify with absorbent package for disposal  N/A
<b>Treatability</b>	Biodegradability: With water prior to cure. Influence on Biological Wastewater Treatment: None Other Impacts on Wastewater Treatment: None Recommended Wastewater Treatment: Dilutable Constituents Interfering With or Not Amenable to Biological or Wastewater Treatment: None	
<b>Recommended Waste Disposal</b>	Dispose of in accordance with Federal, State and Local guidelines.	

**EMERGENCY & INFO: 1-800-423-7264**

*Form based on O.S.H.A. Form 20. Information presented herein has been compiled from sources to be reliable and is accurate and reliable to be the best of our knowledge and belief but is not guaranteed to be so.*

**EMERGENCY & INFO: 941-753-7500**